

Polyethylene terephthalate (PET)

RENATUS®

C3030FA

HB, Standard

General Properties of C3030FA

table1-1 General Properties (ISO)

Item	Unit	Test Method	HB, Standard
			C3030FA
			GF Reinforced, Natural Color
Color			-
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>PET-GF30<
Density	g/cm ³	ISO 1183	1.6
Water absorption (23°C,24hrs,1mmt)	%	ISO 62	0.2
Tensile strength	MPa	ISO 527-1,2	147
Strain at break	%	ISO 527-1,2	1.8
Flexural strength	MPa	ISO 178	241
Flexural modulus	MPa	ISO 178	10,400
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	8.3
Temperature of deflection under load (1.8MPa)	°C	ISO 75-1,2	238
Coefficient of linear thermal expansion (Normal temperature, Flow direction)	x10 ⁻⁵ /°C	Our standard	-
Coefficient of linear thermal expansion (Normal temperature, Transverse direction)	x10 ⁻⁵ /°C	Our standard	-
Electric strength (3mmt)	kV/mm	IEC 60243-1	21
Volume resistivity	Ω·cm	IEC 60093	6 × 10 ¹⁶
Tracking resistance (CTI)	V	IEC 60112	200
Flammability		UL94	HB
The yellow card File No.			E213445
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

NOTES TO USERS

- Consult the appropriate technical data or Safety Data Sheet(SDS) for proper use of RENATUS® PET.
- Dry pellets before molding. Pre-dry pellets by a dehumidification dryer at 130 - 140°C for more than 5 hours. (Max. 24 hours)
It is also advisable to use a hopper dryer to keep pellets dry during molding.
- Optimum material temperatures: 270 - 290°C (Non-flame retardant grade), 265 - 280°C (Flame retardant grade)
[Do not heat the material above 300°C]
- In case of decomposition of the material or any fear of decomposition, lower the cylinder temperature and purge (discharge) the material from the cylinder.
- During purging, wear safety goggles and keep your hands and face away from the nozzle section.
- Keep the workplace ventilated locally or entirely during operation.
- To prevent the danger of slip and environmental hazard, rake the spilled pellets and place them in proper containers for disposal.

RENATUS® is a registered trademark of Polyplastics Co.,Ltd. in Japan and other countries.

POLYPLASTICS CO., LTD.

JR Shinagawa East Bldg.,
18-1, Konan 2-chome, Minato-ku, Tokyo, 108-8280 Japan
Tel: +81-3-6711-8610 Fax: +81-3-6711-8618

<http://www.polyplastics.com/en/>